

Product data sheet

TEXTURAN

Polyester continuous filament, texturised

- developed to be used in combination with Topfil
- the functional underthread for mattress production



Technical data:

Ticket no.	Tex no.	Linear density (dtex) (DIN EN ISO 2060)	Linear density (Nm) (DIN EN ISO 2060)	Breaking force (cN) (DIN EN ISO 2062)	Elongation at break (%) (DIN EN ISO 2062)	Needle size Nm	Needle size No.
100	35	190 * 2	53 / 2	1436	27	90-110	14-18
120	18	188 * 1	53 / 1	711	26	80-90	12-14

Thermal properties:

- Melting point : ~ 250-260 °C

Article assortment:

Ticket no.	Tex no.	Article no.	Make-up	Spool type	No. of colours
100	35	8392	10.000 m	FS	1
100	35	8393	20.000 m	FS	1
120	18	8538	20.000 m	FS	1

Available colour no.: 1000 = raw white

Main application:

- Mattresses
- Pillows & quilts



Certifications and special testings:

